


DIMENSIONES / Dimensions / Dimensions



CARACTERÍSTICAS MECÁNICAS / Mechanical features / Caractéristiques mécaniques

Acero Steel Acier	Espesor Thickness Épaisseur (mm)	Área Area Région (cm ² /m)	Peso Weight Poids (kg/m ²)	I _z (cm ⁴ /m)	I _y (cm ⁴ /m)	V _y (cm)	V _{py} (cm)	Wyinf (cm ³ /m)	Wysup (cm ³ /m)	Mrd (KNm/m)	Nrd (KN/m)
S250	0,80	12,79	10,04	7.988,18	1.016,14	10,20	14,85	99,67	68,42	17,11	319,68
	0,90	14,39	11,30	8.986,71	1.143,16	10,20	14,85	112,13	76,98	19,24	359,63
	1,00	15,98	12,56	9.985,24	1.270,18	10,20	14,85	124,59	85,53	21,38	399,62
	1,25	19,98	15,69	12.481,54	1.587,73	10,20	14,85	155,74	106,91	26,73	499,53
	1,50	23,98	18,83	14.977,86	1.905,28	10,20	14,85	186,88	128,29	32,07	599,40
S280	0,80	12,79	10,04	7.988,18	1.016,14	10,20	14,85	99,67	68,42	19,16	358,04
	0,90	14,39	11,30	8.986,71	1.143,16	10,20	14,85	112,13	76,98	21,55	402,79
	1,00	15,98	12,56	9.985,24	1.270,18	10,20	14,85	124,59	85,53	23,95	447,58
	1,25	19,98	15,69	12.481,54	1.587,73	10,20	14,85	155,74	106,91	29,93	559,47
	1,50	23,98	18,83	14.977,86	1.905,28	10,20	14,85	186,88	128,29	35,92	671,33
S320	0,80	12,79	10,04	7.988,18	1.016,14	10,20	14,85	99,67	68,42	21,90	409,19
	0,90	14,39	11,30	8.986,71	1.143,16	10,20	14,85	112,13	76,98	24,63	460,33
	1,00	15,98	12,56	9.985,24	1.270,18	10,20	14,85	124,59	85,53	27,37	511,52
	1,25	19,98	15,69	12.481,54	1.587,73	10,20	14,85	155,74	106,91	34,21	639,40
	1,50	23,98	18,83	14.977,86	1.905,28	10,20	14,85	186,88	128,29	41,05	767,23